

Ultramid® B3WM8 BK00102

Polyamide 6



Product Description

Ultramid B3WM8 BK00102 is a heat stabilized, pigmented black, 40% mineral reinforced PA6 injection molding resin. It possesses high stiffness, dimensional stability and heat resistance combined with excellent processability including low warp and resistance to sink-mark formation. It maintains its inherent chemical resistance to greases, oils and hydrocarbons.

Applications

Ultramid B3WM8 BK00102 is generally recommended for applications such as marine hardware, brackets, fittings, bobbins, office furniture, appliance components, and power tool housings.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm ³	1183	1.49	
Moisture, %	62		
(24 Hour)		1.1	
(50% RH)		1.6	
(Saturation)		5.7	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
-40C		8,310	7,700
23C		6,400	3,800
80C		1,360	1,400
120C		970	1,200
150C		910	840
Tensile stress at break, MPa	527		
-40C		135	135
23C		85	60
80C		40	35
120C		30	27
150C		20	20
Tensile strain at break, %	527		
-40C		6.0	5.0
23C		10	30
80C		35	30
120C		40	40
150C		40	60
Flexural Strength, MPa	178		
23C		140	50
Flexural Modulus, MPa	178		
23C		5,200	2,100
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²	180		
23C		6	-
Charpy Notched, kJ/m ²	179		

23C		3	-
Charpy Unnotched, kJ/m ²	179		
23C		130	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	220	-
HDT A, C	75	90	-
HDT B, C	75	190	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Volume Resistivity (Ohm-m)	IEC 60093	>1E13	-

Processing Guidelines

Material Handling

Max. Water content: 0.15%
 Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C). Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 270-295C (518-563F)
 Mold Temperature 80-95C (176-203F)
 Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95C (176-203F) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.